



PACIFIC REFRACTORIES



PACARB™

CARBON BRICKS	
CHARACTERISTICS	PACARB III
Bulk Density (g/cc)	Min. 1.5
Cold Crushing Strength (Kg/cm ²)	Min. 450
Flexural Strength (Kg/cm ²)	Min. 120
App. Porosity (%)	Max. 18
Carbon Content (%)	Min. 96
Ash Content (%)	Max. 2
Service Temperature (°C)	≤180

Storage: To be stored under shade, in a cool and dry place.

Notes: Tailor-made specifications are also available as per process requirements.

The data given above are based on average of test results on sample from routine plant production by standard testing procedures. Variation from above data may occur during individual tests. This does not constitute a guarantee figure. For best results please refer to our instructions for application OR contact our representative for guidance. The suggested use assumes that all precautions and safety measures are taken care by the user.

For more information, please contact: Office: C-16/3, TTC, MIDC Area, Pawane, Thane-Belapur Road, Navi-Mumbai, 400705. India. info@pacificrefractories.com

www.pacificrefractories.com